



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

DAP® TOUCH 'N FOAM PROFESSIONAL SPRAY FOAM KITS 15, 200 & 600 Low GWP – Cream

PRODUCT DESCRIPTION

DAP® Touch 'n Foam® Professional Spray Foam Kits 15, 200 & 600 Low GWP are portable, self-contained dispensing systems. These spray foam kits are formulated to meet low Global Warming Potential (GWP) requirements and includes no HFC's. When used according to manufacturer's directions, these systems effectively air seal and insulate homes and buildings while enhancing R-value. Spray Foam Kits are low pressure, permanent and dry in 60 seconds. Spray Foam Kits use disposable, pressurized chemical cylinders that dispense polyurethane spray foam, eliminating the need for external air compressors, pumping equipment or dry nitrogen. These Spray Foam Kits provide quick and easy foam application for repairs and renovations, new installations and production applications.



15 Kit

Kit includes Applicator, Nozzles, Gloves, Glasses and Wrench



200 Kit



600 Kit

PACKAGING	Case	COLOR	UPC
16 oz. Cans (TK15 Kit)	1 Kit	Cream	075650025154
10 lb Cylinders (200 Kit)	1 kit	Cream	075650292006
40 lb Cylinders (600 Kit)	1 kit	Cream	075650295991



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

KEY FEATURES & BENEFITS

- Where sold, complies with State HFC regulations
- Contains no HFC's
- ICC Evaluation Service Listed ESR 3052
- Foam dries in 60 seconds
- Fully portable
- Class A fire-rated
- Closed cell structure
- Resists moisture that can lead to mold or mildew
- Bonds to a variety of materials including wood, masonry, metals, and drywall
- Seals out air and moisture saving on energy costs all year round
- High R-Values
- Interior / exterior use

SUGGESTED USES

USE TO FILL AND SEAL:

- Rim joists
- Basements
- Attics
- Crawlspace
- Foundations
- Ducting

FOR BEST RESULTS

- Apply in temperatures between 60°F- 90°F (16°C – 32°C)
- Surface must be clean, dry, and free of all foreign material for adhesion

APPLICATION

DIRECTIONS: Important – read all directions and cautions before use. Always wear gloves, eye protection and work clothes. Use drop cloths. Product is flammable during dispensing – turn off sources of ignition prior to use

Preparation: To promote adhesion, surface must be clean, dry, and free of all foreign material. All substrate surfaces should be clean/dry and above 60°F (16°C) prior to application. Variance outside of the recommended temperature can drastically affect the adhesion and yield of your foam kit.



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

Application: Refer to “2-Component Polyurethane Spray Foam Instructions for Use” found inside the product carton. **IMPORTANT: CHECK 3 TEMPERATURES.**

IMPORTANT: CHECK 3 TEMPERATURES.
Low temperatures can affect foam performance.

CHEMICALS	SURFACES	AIR
↑ 70°F/21°C (70°-90°F/21°-32°C)	↑ 60°F/16°C (60°-90°F/16°-32°C)	↑ 60°F/16°C (60°-90°F/16°-32°C)

Clean-up: If wet foam contacts skin, clean immediately with a dry rag – do not use water – water accelerates curing. Cured foam must be removed mechanically from surfaces. Uncured foam can be cleaned from most surfaces with Foam Cleaner or acetone. If foam dries on skin, apply generous amounts of petroleum jelly, put on plastic gloves and wait 1 hour. With a clean cloth, firmly wipe off residue and repeat process if necessary. DO NOT use acetone or other solvents to remove product from skin.

Storage & Disposal. Keep container tightly closed in a cool, well-ventilated area. Store upright below 90° F (33°C). Do not expose containers to conditions that may damage, puncture, or burst the containers. Dispose of leftover material / containers in accordance with Federal, state, and local regulations. See SDS for more information.

TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Theoretical Yield / Output* (15/200/600)	Up to 15 board feet (1.46m ² @25mm) Up to 200 board feet (18.88m ² @ 25mm) Up to 600 board feet (56.64m ² @25mm)
Dry Time/ Tack Free	30 - 60 seconds
Cure Time	Approx. 1 hour
Shelf Life	12 months. Expiration date on box
Application Temperature Range	60°F - 100°F (16°C ~ 38°C)
Cutable	5 minutes
ASTM E84 Surface Burning Characteristics (Flame/Smoke)	15 / 400@ 2"
ASTM D1622 Density (Core) (in place)	1.75 +/- .25pcf (28.0 +/- 4.0kg/m ³) 2.06 +/- .25pcf (33.0 +/- 4.0kg/m ³)
ASTM D6226 Closed Cell Content	>90%
International Residential Code	Compliant
California Bureau of Home Furnishings & Insulation	Listed



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

ASTM C518 Aged R-Value, 1 1/2"	6.6 / 13.3
ICC Evaluation Service Listed	ESR 3052
ASTM E-2178 Air Permeance	<0.004 CFM / ft ² (<0.02 L/s/m ²)
ASTM D1621 Compressive Strength	31 psi (214 kPa)
ASTM E-96 Water Vapor Transmission	0.83 perm @2" (47.4 ng/Pa s m ²)
ASTM D1623 Tensile Strength	24.2 psi (167 kPa)

*A board foot is defined as a 12" x 12" square at 1" thick. Actual output can be affected by a number of factors including temperature and humidity. The theoretical yield has become an industry standard for identifying certain sizes of 2-component kits. Theoretical yield calculations are performed in perfect laboratory conditions, without taking into account the loss of blowing agent or the variations in application method and types.

SAFETY

See product label or Safety Data Sheet (SDS) for health and safety information. You can request an SDS by visiting our website at dap.com or calling 888-DAP-TIPS.

WARRANTY

DAP Canada, DAP Products Inc. and their respective affiliates will not accept liability for more than replacement product or sales price refund under any circumstances.

COMPANY IDENTIFICATION

Manufactured for: DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON, M1X 1B7

Usage Information: Call 888-DAP-TIPS or visit dap.ca & click on "Ask the Expert"

Order Information: 800-668-9397 or 416-321-1522

Fax Number: 416-321-3325

Also visit the DAP website at dap.ca

9/1/2019



TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224



Evaluation Report # ESR-3052



Intertek

WN 20605

Fire Tests Results from Element Lab:
ULC-S102 Per CAN/ULC S711.1 (2019)
12 FSV/160 SDV

Résultats d'essai de résistance au feu d'Element Lab:
ULC-S102 par CAN/ULC S711.1 (2019)
12 FSV/160 SDV

Intertek Testing Services NA Inc. – Warnock Hersey – QUA1673 – (604) 520-3321